AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400


TEST REPORT

Client : Inspired Floorcoverings
Level 1, Suite 3, 72 Terrigal Esplanade
Terrigal NSW 2260

Test Number : 24-004598
Issue Date :
Print Date : 9/12/2024

Sample Description

Clients Ref : "Aura Dusk"
Multi level loop pile carpet tile with cushion backing
End Use : Flooring
Nominal Composition : Nylon, Glass layer, Polyethylene, Cushion
Nominal Mass per Unit Area/Density : 480g/m2
Nominal Thickness : 8mm



© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

0204/11/06

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Inspired Floorcoverings
Level 1, Suite 3, 72 Terrigal Esplanade
Terrigal NSW 2260

Test Number : 24-004598
Issue Date :
Print Date : 9/12/2024

AS/NZS 2111.4-1996 **Surface Pile Mass at Standard Conditions**

Date of Testing	09/12/2024	
Corrected Surface Pile Mass, mean	404	g/m²
Standard Allowance	5.75	%
Specimen		
1	394	g/m²
2	371	g/m²
3	427	g/m²
4	397	g/m²
5	399	g/m²
6	412	g/m²
Mean	400	g/m²
Coefficient of Variation	4.7	%
Moisture Regain of Pile	4.6	%

Modified: Corrected for moisture regain only.

Based on nominal pile fibre content.

Apparatus: Band knife

Due to variation within the specimens tested the coefficient of variation reported is greater than the standard specifies.

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Inspired Floorcoverings
Level 1, Suite 3, 72 Terrigal Esplanade
Terrigal NSW 2260

Test Number : 24-004598
Issue Date :
Print Date : 9/12/2024

AS 2001.3.4-1995 Test A — **Determination of Extractable Matter**

Date of Testing	04/12/2024
Mean	1.0 %
Solvent	Dichloromethane

AS/NZS 2111.9-1996 — **Determination of Number of Tufts per unit Length**

Date of Testing	09/12/2024
S (Parallel to Selvedge) (Stitches)	44.0 / 100mm
G (Right Angles to Selvedge) (Gauge)	48.1 / 100mm

AS/NZS 2111.5-1996 — **Determination of Pile Thickness above the backing - ACCS Modified**

Date of Testing: 09/12/2024

	1	2	3	4	Mean	
Total Thickness	9.5	9.5	9.4	9.5	9.5	mm
Backing Thickness	6.5	6.6	6.5	6.5	6.5	mm
Pile Thickness	3.0	2.9	2.9	3.0	3.0	mm

Template used to facilitate thickness measurement.

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Inspired Floorcoverings
Level 1, Suite 3, 72 Terrigal Esplanade
Terrigal NSW 2260

Test Number : 24-004598
Issue Date :
Print Date : 9/12/2024

TWC 251/247/284-2009 **Texture and Colour Change - Hexapod Tumbler Tester**

Date of Testing		06/12/2024	
After 1500 cycles	Texture	Colour	
Mean Grade	4.5	4.5	
Mean Worst Angle	4.5	4.5	
Pile Thickness Loss		0.4	mm
Pile Thickness Loss		13.4	%
After 8000 cycles	Texture	Colour	
Mean Grade	3.5	4.0	
Mean Worst Angle	3.5	4.0	
Pile Thickness Loss		1.2	mm
Pile Thickness Loss		40.8	%
Total Carpet Thickness		9.5	mm
Total Pile Thickness		3.0	mm
International Reference Scale		E	

Vacuum cleaned with upright cleaner at commencement of test, after 1500 cycles and where applicable every 2000 cycles. Thickness measurements taken after vacuuming.

Rating scale: 1 = Very severe change 5 = No change

NATA Accreditation does not cover the performance of TWC 284

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Inspired Floorcoverings
Level 1, Suite 3, 72 Terrigal Esplanade
Terrigal NSW 2260

Test Number : 24-004598
Issue Date :
Print Date : 9/12/2024

AS 2404-1980
(ACCS Modified)

Fire Propogation Properties (AS 2111.18 Pill Test)

Date of Testing 04/12/2024

Pass

Samples were conditioned in standard atmosphere of 20±2°C and 65±2% relative humidity prior to testing.

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Chris Campbell
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR