Slip Check to AS 4586-2013

The Knit Range

Report Number: R35062
Report Date: 15 January 2026
Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by	**Prepared for**	**Approved by**
Safe Environments Pty Limited 6/7 Inglewood Place Norwest NSW 2153	Inspired Floor Coverings 51 Tramway Road North Avoca NSW 2260	Mathew Sutton Authorised Signatory

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

6/7 Inglewood Place
Norwest NSW 2153
Phone02 9621 3706
info@SafeEnvironments.com.au

15 January 2026

Test Report No. R35062

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Inspired Floor Coverings
Client Address:	51 Tramway Road North Avoca NSW 2260
Product Manufacturer:	Supplied by Inspired Floor Coverings
Product Description:	The Knit Range
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	6/7 Inglewood Place, Norwest NSW 2153
Conducted by:	Nathan Phanith

Date:	15 January 2026	Temperature:	27°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	N/A		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	78	78	78	77	79

Reported SRV of Sample:	**78^**
Class:	**P5^**

^ Surface Tested Dry

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd